

CcLashes
Strandvejen 153, 1 tv.
2900 Hellerup
DENMARK

Eurofins Product Testing A/S
Smedeskovvej 38
8464 Galten
Denmark

CustomerSupport@eurofins.dk
www.eurofins.dk/dk/product-testing


TEST REPORT

11 Maj 2021

1 Sample Information

Sample name	Magnetic lashes
Sample reception	20/04/2021
Sample no.	392-2021-00192801
Analysis period	26/04/2021 - 11/05/2021

2 Picture of Sample



Eurofins Product Testing A/S

*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit www.eurofins.dk/uncertainty

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

⌘: Internal test method

n.d: Not detected

n.m: Not measurable

LOQ: Limit of quantification

3 Applied Test Methods

3.1 General Test References

Method	Parameter	Analysis principle	LOQ	Um(%)
EN 1811:2015-10 ¹	Preparation for migration	Exposure to sweat simulant	-	-
EN 1811:2015-10 ¹	Nickel release	ICP-MS	0.1 µg/cm ²	< 46%

3.2 Test Conditions

Simulant	Protected surface which is not a sample surface	Area exposed [cm ²]	Volume (Simulant) [mL]	Migration Conditions
Sweat	No	2	5	7 days at 30°C

4 Results

4.1 Specific Migration

Parameter	CAS No.	Simulant	Result [µg/cm ²]
Nickel (Ni)	7440-02-0	Sweat	< 0.1

5 Version History

Report date	Report number	Modification
11/05/2021	392-2021-00192801_XN_EN	Current version

¹ Eurofins Consumer Product Testing GmbH : DIN EN ISO/IEC 17025:2018 DAKKS D-PL-14435-01-00

*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit www.eurofins.dk/uncertainty

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.